



International Sulphur, Inc.

ISO 9001:2000

Mt. Pleasant, Texas 75456-0611

P.O. Box 611
903-577-5500
FAX: 903-577-5540

TECHNICAL DATA

RED BALL RUBBERMAKERS MC SULFUR

PRODUCT NUMBER:	75798								
FORMULA:	S ₈								
TRADEMARK:	RED BALL								
NOMENCLATURE:	SULPHUR								
CAS NUMBER:	7704-34-9								
CAS INDEX NAME:	SULPHUR								
GRADE:	RUBBERMAKERS MC TREATED								
DESCRIPTION:	A rubbermakers sulphur with conditioning agent added to increase flowability. Oil addition to minimize dust added per request.								
SPECIFICATIONS:	<table><tr><td>Purity (oil free)</td><td>97.5 Min.</td></tr><tr><td>Ash</td><td>2.10 Max</td></tr><tr><td>Acidity (as H₂SO₄), % WT</td><td>0.01 Max.</td></tr><tr><td>Heat Loss, % WT</td><td>.15 Max.</td></tr></table>	Purity (oil free)	97.5 Min.	Ash	2.10 Max	Acidity (as H ₂ SO ₄), % WT	0.01 Max.	Heat Loss, % WT	.15 Max.
Purity (oil free)	97.5 Min.								
Ash	2.10 Max								
Acidity (as H ₂ SO ₄), % WT	0.01 Max.								
Heat Loss, % WT	.15 Max.								
PHYSICAL:	<table><tr><td>Passing 100 Mesh</td><td>99.9 Min.</td></tr><tr><td>Passing 325 Mesh</td><td>98 Min.</td></tr></table>	Passing 100 Mesh	99.9 Min.	Passing 325 Mesh	98 Min.				
Passing 100 Mesh	99.9 Min.								
Passing 325 Mesh	98 Min.								
CONTAINERS:	50 lb Net Weight Paper Bags								

December 1, 2004

Jerry J. Jennett