



CureRite[®] TBzD

Technical Data Sheet

Description

Tetrabenzylthiuram disulfide

Molecular Weight:

Product Specification

- Heat Loss, % (85°, 1.5 hours)
- Melting Point, °C
- Ash, %
- Assay, %
- Color

Specification

2.5 Maximum
130-135°C
0.5 Maximum
95% Minimum
White to Cream

Test Method

T-138
T-139
T-137
HPLC

Form

- Powder

Packaging

- Bag, 55 lbs.

Characteristics

- Low to no nitrosamine; not carcinogenic
- Longer scorch times

Application

- Fast curing primary or secondary accelerator in NR, SBR, NBR