



product data sheet

Sasobit LM

Code 1656 Revision 2 21 July 2015

Properties	Test method	Units	Specification	Typical values
Congealing point	ASTM D 938	°C	96-100	97
Drop melting point	ASTM D 3954	°C	-	112
Penetration at 25°C	ASTM D 1321	0.1 mm	3 max	1
Penetration at 65°C	ASTM D 1321	0.1 mm	25 max	23
Colour	Sasol 2000	ASTM	1.5 max	1.5
MIBK solubles	ASTM D 721	mass %	1.5 max	1.2

Compliance

F&DA: This product complies with the requirements of 21 Code of Federal Regulations: Parts 175.105(Adhesives), 177.1390 (Laminate Structures).

Packaging

Sasobit LM is supplied in the form of pastilles packed in 20kg PE bags or 600kg Jumbo bags.

Note

Due to the nature and application of these products the storage life is limited. Therefore, to obtain the best performance from the product, we recommend use within 5 years from sample date on the Certificate of Analysis.

Notice This product information is indicative and does not include any guarantee

Sasol Chemicals a division of Sasol South Africa (Pty) Ltd.
ISO 9001/ISO 14001