



## product data sheet

### SASOBIT

Code 1596    Revision 12    18 July 2013

Properties	Test method	Units	Specification	Typical values
Congealing point	ASTM D 938	°C	100 min	101
Penetration at 25 °C	ASTM D 1321	0.1 mm	1 max	<1
Penetration at 65 °C	ASTM D 1321	0.1 mm	13 max	11
Brookfield viscosity at 135 °C	Sasol Wax 011	cP	10 – 14	12

#### Compliance

F&DA: This product complies with the requirements of 21 Code of Federal Regulations: Parts 175.105(Adhesives), 177.1390 (Laminate Structures).

#### Note

Due to the nature and application of these products the storage life is limited. Therefore, to obtain the best performance from the product, we recommend use within 10 years from sample date on the Certificate of Analysis.

**Notice**      **This product information is indicative and does not include any guarantee**

**Sasol Wax (South Africa) a division of Sasol Chemical Industries Limited**  
ISO 9001/ISO 14001