

## product data sheet

### SASOBIT REDUX

Code 7550    Revision 0    07 June 2017

Properties	Test method	Units	Specification	Typical values
Congealing point	ASTM D 938	°C	72 - 83	78
Penetration at 25°C	ASTM D 1321	0.1 mm	16 - 30	20

#### **Packaging**

Sasobit Redux is supplied in the form of pastilles packed in 20kg PE bags or 500kg Jumbo bags.

#### **Note**

To obtain the best performance from the product, we recommend use within 5 years from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C.

**Notice**      **This product information is indicative and does not include any guarantee**

Sasol Chemicals a division of Sasol South Africa (Pty) Ltd.  
ISO 9001/ISO 14001